



CONSUMER PRODUCTS SERVICES DIVISION

CARPENTERS MANUFACTORY LIMITED

Technical Report: (8520)020-0189

March 17, 2020

Date Received: January 21, 2020

Page 1 of 81

CARPENTERS MANUFACTORY LIMITED
HUANG JIN JI INDUSTRIAL ZONE, SHANG JIE
VILLAGE, QI SHI TOWN, DONG GUAN CITY, GUANG
DONG PROVINCE, P.R.CHINA

Sample Description: A - WALL ELEMENTS - GIANT FUN MIRROR
B - BEE HIVE MEMORY TRAINING GAME(6 THEMES)
C - LACING & WEAVING BOARD
D - EMOTIONS LEARNING GAME
E - BASIC SKILLS TRAINING - T - SHIRT AND SHOE
F - MOSAIC TILES

Vendor: CARPENTERS MANUFACTORY LIMITED 东莞天志木制品有限公司 Sample Size: 12

Manufacturer: N/A Style No(s): ME15129, MK14153, MK14252, MK15211, ME09494, ME14573

Buyer: N/A SKN/SKU No.: N/A
Labeled Age Grade: FOR A-C, E-F = 3 YEARS+, FOR PO No.: N/A
D = 3 YEARS+/AGES 2Y+

Appropriate Age Grade: NOT REQUESTED Ref #: N/A
Client Specified Age Grade: 3+ Country of Origin: CHINA

Tested Age Grade: OVER 3 YEARS OF AGE Assortment No.: N/A
UPC Code: 6955920015129, 6955920014153, Country Of Destination: GLOBAL
6955920014252, 6955920015211,
6955920009494, 6955920014573



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 2 of 81

EXECUTIVE SUMMARY:

The sample(s) MEET the following requirement(s):

- The flammability requirements of 16 CFR 1500.3(c)(6)(vi), "Flammable solid" (FHSA regulations).
- Labeling requirements of "CE marking, manufacturer/ Importer name and address, and product identification" under "Directive 2009/48/EC Safety of Toy".
- The migration of certain elements requirements of the AS/NZS Standard, "Safety of toys", AS/NZS 8124: Part 3: 2012 with Amendment No. 1: 2016.
- The labeling requirements of the tested subclauses of the Australian/New Zealand Standard, "Safety of toys", AS/NZS ISO 8124: Part 1: 2019.
- The mechanical and physical properties requirements of the tested subclauses of the Australian/New Zealand Standard, "Safety of toys", AS/NZS ISO 8124: Part 1: 2019.
- The flammability requirements of the AS/NZS Standard, "Safety of toys", AS/NZS 8124: Part 2: 2016.
- The labeling requirements of ASTM F963-17, "Standard consumer safety specification for toy safety".
- The mechanical hazards requirements of ASTM F963-17, "Standard consumer safety specification for toy safety".
- The soluble heavy metals content in surface coating requirements of ASTM F963-17, "Standard Consumer Safety Specification for Toy Safety," Section 4.3.5.1(2).
- The soluble heavy metals content in substrate requirements of ASTM F963-17, "Standard Consumer Safety Specification for Toy Safety," Section 4.3.5.2(2)(b).
- The applicable heavy metals content requirements for surface coatings of the Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 Sec. 23 with Amendment in SOR/2016-195.
- The flammability requirements of Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 section 32.
- The mechanical hazards requirements of the tested sections of Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 and Schedule 2.
- The total lead content requirements of the Canada Consumer Product Safety Act, Consumer Products Containing Lead Regulations SOR/2018-83.
- The phthalates (BBP, DBP, DEHP, DINP, DIBP, DPENP, DHEXP & DCHP) content requirements of the Consumer Product Safety Improvement Act (CPSIA) of 2008 Sec. 108(a) and 108(c), 16 CFR 1307).
- The total lead content of 100ppm requirements by composite testing in substrate materials (Consumer Products Safety Improvement Act (CPSIA) of 2008).
- The total lead content of 90ppm requirements of 16 CFR 1303, "Ban of lead-containing paint and certain consumer products bearing lead-containing paint" as mandated by Congress in section 101(f) of the Consumer Products Safety Improvement Act (CPSIA) of 2008, Public Law 110-314.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 3 of 81

EXECUTIVE SUMMARY:

The sample(s) MEET the following requirement(s):

- The cellulose nitrate requirements of Canada Toys Regulations, SOR/2011-17, section 21.
- The listed aromatic amines (azocolourants) content requirement of the European Regulation (EC) No. 1907/2006 of the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), Annex XVII concerning the Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles, Item no. 43, Points 1 and 2.
- The BBP, DBP DEHP and DIBP content requirements of the European Regulation (EC) No. 1907/2006 of the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), Annex XVII concerning the Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles, Item no. 51 (amended up to EU No. 2018/2005).
- The BBP, DBP and DEHP content requirements of the European Regulation (EC) No. 1907/2006 of the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), Annex XVII concerning the Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles, Item no. 51.
- The cadmium content requirement of the European Regulation (EC) No. 1907/2006 of the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), Annex XVII concerning the Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles, Item no. 23 (amended up to EU No. 2016/217).
- The DNOP, DINP and DIDP content requirements of the European Regulation (EC) No. 1907/2006 of the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), Annex XVII concerning the Restrictions on the manufacture, placing on the market and use of certain dangerous substances, preparations and articles, Item no. 52.
- The mechanical and physical properties requirements of the tested subclauses of the European Standard, "Safety of toys", EN71: Part 1:2014+A1:2018, clauses 1-7.
- The flammability requirements of the European Standard "Safety of Toys", EN 71: Part 2: 2011+ A1: 2014.
- The formaldehyde release requirement in accessible resin-bonded wood components of the European Standard, "Safety of Toys: Organic Chemical Compounds - Requirement", EN 71: Part 9: 2005, and Amendment A1: 2007, when tested according to the method BS EN 717-3.
- The migration of certain elements requirements of the European Standard, "Safety of Toys", EN 71 Part 3: 2019.
- The migration of certain elements in Category III - Scraped off toy material requirements of the European Standard, "Safety of Toys", EN 71 Part 3: 2013+A3:2018.
- The 17 phthalates content requirements of the client's specifications.

Note: The sample(s) was not evaluated to the Normal Use testing requirements specified in ASTM F963-17, Section 8.5. It is the responsibility of the manufacturer, vendor or distributor to conduct tests that will simulate normal use conditions. These tests shall ensure that hazards are not generated through normal wear and deterioration of the sample(s). These tests shall also simulate the normal play mode of the toy and to simulate the expected mode of use of the particular toy. The tests shall be conducted in an expected use environment. These normal use tests shall simulate the intended use of the toy based on its estimated lifetime.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 4 of 81

EXECUTIVE SUMMARY:

- Note: At the request of the client, the sample(s) was evaluated for use by children 3+.
- Note: The manufacturer / importer information was present on the packaging only. It has to be noted that, according to TSD 2009/48/EC, the manufacturers/ importer shall indicate their name, registered trade name or registered trade mark and the address at which they can be contacted on the toy, or, where that is not possible, on its packaging or in a document accompanying the toy.
- Note: The product identification is present on the packaging only. It has to be noted that, according to TSD 2009/48/EC, manufacturers shall ensure that their toys bear a type, batch, serial or model number or other element allowing their identification, or, where the size or nature of the toy does not allow it, that the required information is provided on the packaging or in a document accompanying the toy.
- Note: The received sample(s) contained specimen of less than 0.2 g by weight on one single sample, therefore such specimen was not subjected to this requirement, according to test method EN14362-1: 2012, Section 8.2.
- Note: According to the associated documents of Consumer Product Safety Improvement Act (CPSIA) of 2008, exemptions were granted to certain materials or products, such as natural materials / paper and similar materials / CMYK process printing inks / metal & alloys / electronics devices components / ordinary books / dyed & undyed textiles. Therefore, the lead content analysis of some components was not conducted.
- Note: The received sample(s) contained accessible material(s) of less than 10 milligrams by weight on one single sample, therefore such material(s) was not subject to the heavy metals analysis of ASTM F963-17, "Standard consumer safety specification on toy safety", Section 4.3.5.1(2) and 4.3.5.2, as specified in Section 8.3.3.6(2) and Section 8.3.5.3(2).
- Note: The received sample(s) contained accessible component(s) of less than 10 milligrams by weight on one single sample, therefore such component(s) was not subject to migration of certain elements requirements of the AS/NZS Standard, "Safety of toys", AS/NZS 8124: Part 3: 2012 with Amendment No. 1: 2016, as specified in Clause 7 – Selection of test portions.
- Note: The received sample(s) contained accessible component(s) of less than 10 milligrams by weight on one single sample, therefore such component(s) was not subject to migration of certain elements of European Standard, "Safety of Toys", EN 71 Part 3: 2013 + A3:2018, as specified in Clause 7.1 - Selection of test portions.
- Note: The received sample(s) contained accessible component(s) of less than 10 milligrams by weight on one single sample, therefore such component(s) was not subject to migration of certain elements of European Standard, "Safety of Toys", EN 71 Part 3: 2019, as specified in Clause 7.1 - Selection of test portions.
- Note: The sample(s) submitted do not fall within the scope of EN 71 PT.9 Formaldehyde in textile / 2009/48/EC Formamide thus the corresponding testing has/have not been conducted.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 5 of 81

EXECUTIVE SUMMARY:

Note: According to ASTM F963-17, "Standard consumer safety specification on toy safety", Annex A11.10.1.5, exemption were granted to paper and paperboard. Therefore, the heavy metals content in substrate analysis of some components of ASTM F963-17, Section 4.3.5.2(2)(b) was not conducted.

BUREAU VERITAS SHENZHEN CO., LTD.

Hon Yin Kan
Manager

Toys And Juvenile Products Department

HK/dk



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 6 of 81

RESULTS:

APPROPRIATE AGE GRADE DETERMINATION

The Appropriate Age Grade is determined with reference to the Age Determination Guidelines of the Consumer Product Safety Commission (CPSC); and the ASTM F963-17, "Standard Consumer Safety Specification for Toy Safety". Annex A1

Note : The most stringent age grade from the Labeled Age Grade and the Appropriate Age Grade will be used for testing.

Note : If the client does not specify an age grade for testing or request Bureau Veritas Consumer Products Services, Inc. to determine an appropriate age grade, the labeled age grade will be used for testing.

USE AND ABUSE TESTS

The samples were undergo the tests in accordance with section 8.6 through 8.16, whichever is applicable

Test	Test Parameters	Standard Reference
Impact Test	4 x 3 ft	1500.53(b)
Torque Test	4 in-lbs	1500.53(e)
Tension Test	15 lbs	1500.53(f)



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 7 of 81

RESULTS:

PHYSICAL AND MECHANICAL HAZARDS (ASTM F963-17)

Section	Requirement	Result
4.1	Material Quality	M
4.3.7	Stuffing Materials	N/A
4.5	Sound-Producing Toys	N/A
4.6	Small Objects	N/A
4.7	Accessible Edges	M
4.8	Projections	M
4.9	Accessible Points	M
4.10	Wires and Rods	N/A
4.11	Nails and Fasteners	M
4.12	Plastic Film	M
4.13	Folding Mechanisms and Hinges	N/A
4.14	Cords, Straps and Elastics	N/A
4.15	Stability and Over-Load Requirements	N/A
4.16	Confined Spaces	N/A
4.17	Wheels, Tires, and Axles	N/A
4.18	Holes, Clearances and Accessibility of Mechanisms	M
4.19	Simulated Protective Devices	N/A
4.20	Pacifiers	N/A
4.21	Projectile Toys	N/A
4.22	Teethers and Teething Toys	N/A
4.23	Rattles	N/A
4.24	Squeeze Toys	N/A
4.25	Battery-Operated Toys (exclude Section 4.25.10 Battery-powered ride-on toys & Section 4.25.11 Toys that Contain Secondary Cells or Secondary Batteries)	N/A
4.26	Toys Intended to be Attached to a Crib or Playpen	N/A
4.27	Stuffed and Beanbag-Type Toys	N/A
4.30	Toy Gun Marking	N/A
4.32	Certain Toys with Nearly Spherical Ends	N/A
4.34	Small Balls	N/A
4.35	Pompoms	N/A
4.36	Hemispheric-Shaped Objects	N/A
4.37	Yo Yo Elastic Tether Toys	N/A
4.38	Magnets	N/A
4.39	Jaw Entrapment in Handles and Steering Wheels	N/A
4.40	Expanding Materials	N/A

M = Meet NM = Not Meet N/A = Not Applicable R = Refer to Comment Section



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 8 of 81

RESULTS:

LABELING AND INSTRUCTIONAL REQUIREMENT (ASTM F963-17)

Section	Requirement	Result
5.4 & 5.3	Aquatic Toys	N/A
5.5 & 5.3	Crib and Playpen Toys	N/A
5.6 & 5.3	Mobiles	N/A
5.7 & 5.3	Stroller and Carriage Toys	N/A
5.8 & 5.3	Toys Intended to be Assembled by an Adult	M
5.9 & 5.3	Simulated Protective Devices	N/A
5.10 & 5.3	Toys with Functional Sharp Edges or Sharp Points	N/A
5.11	Small Objects, Small Balls, Marbles and Balloons (16 CFR 1500.19)	N/A
5.12	Toy Caps (16CFR1500.86)	N/A
5.13	Art Materials (16 CFR 1500.14(b)(8))	N/A
5.15	Battery-Operated Toys (exclude 5.15.1 and 5.15.2)	N/A
5.15.1 & 5.3	Battery-Powered Ride-On Toys	N/A
5.15.2 & 5.3	Button or Coin Cell Batteries	N/A
5.16	Promotional Materials	M
5.17 & 5.3	Magnets	N/A
6.1	Definition and Description	M
6.2	Crib and Playpen Toys	N/A
6.3	Mobiles	N/A
6.4 & 5.3	Toys Intended to be Assembled by an Adult	N/A
6.5	Battery-Operated Toys	N/A
6.6	Battery-Powered Ride-On Toys	N/A
6.7	Toys in Contact with Food	N/A
7.1	Producer's Name and Address	M
7.2	Battery-Powered Ride-on Toys	N/A

M = Meet NM = Not Meet N/A = Not Applicable R = Refer to Comment Section

FLAMMABILITY (16 CFR SECTION 1500.3(c)6)(vi))

Requirement	Test Method Reference	Findings
Burn rate no greater than 0.1 of an inch per second	16 CFR 1500.44	Did not ignite.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 9 of 81

RESULTS:

APPROPRIATE AGE GRADE DETERMINATION

The Appropriate Age Grade is determined with reference to the EN71: Part 1 : 2014 +A1:2018, CEN ISO/TR 8124-8:2016 Safety of toys - Part 8: Age Determination Guidelines prepared by Technical Committee CEN/TC 52 and Age Grade Determination Guidelines of the Consumer Product Safety Commission (CPSC).

Note : The most stringent age grade from the Labeled Age Grade and the Appropriate Age Grade will be used for testing.

Note : If the client does not specify an age grade for testing or request Bureau Veritas Consumer Products Services, Inc. to determine an appropriate age grade, the labeled age grade will be used for testing.

EXPLANATION OF THE ABBREVIATIONS FOR PART 1, 2 & 6

Symbol	Explanation				
NM	The sample(s) DOES NOT MEET the requirement of this Subclause				
M	The sample(s) MEETS the requirement of this Subclause				
N/A	Not Applicable				
NR	Not Requested				
NE	Not Evaluated				
NT	Not Tested				
NP	None Present				
P	Present				
R	Refer to Comment Section of this report				
Symbol	Language Present	Symbol	Language Present	Symbol	Language Present
B	Belgian language	G	German language	PR	Portuguese language
D	Danish language	GR	Greek language	S	Spanish language
E	English language	H	Dutch language	SD	Swedish language
F	Finnish language	I	Italian language	SZ	Swiss language
FR	French language	N	Norwegian language		

RESULTS:

**MECHANICAL & PHYSICAL PROPERTIES
(EN 71: PART 1 – 2014+A1 – 2018)**

Subclause	Requirement	Result
4.1	Material cleanliness	M
4.2	Assembly	M
4.3	Flexible plastic sheeting	NA
4.4	Toy Bags	NA
4.5	Glass	NA
4.6	Expanding materials	NA
4.7 & 7.6	Edges	M
4.8 & 7.6	Points and metallic wires	M
4.8e	Splinters	M
4.9	Protruding parts	M
4.10.1	Folding and sliding mechanisms	NA
4.10.2	Driving mechanisms	NA
4.10.3	Hinges	NA
4.10.4	Springs	NA
4.11	Mouth actuated toys and other toys intended to be put in the mouth	NA
4.12 & 7.3	Balloons	NA
4.13 & 7.9	Cord of toy kites and other flying toys	NA
4.14.1	Toys which a child can enter	NA
4.14.2 & 7.8	Masks and helmets	NA
4.15.1	Toys propelled by child	
4.15.1.2 & 7.10.1 & 7.10.2 & 7.10.3 & 7.10.4 & 7.16	Toys propelled by child – Instructions for use	NA
4.15.1.3	Toys propelled by child – Strength	NA
4.15.1.4	Toys propelled by child – Stability	NA
4.15.1.5	Toys propelled by child – Braking	NA
4.15.1.6	Toys propelled by child - Transmission	NA
4.15.1.7	Toys propelled by child – insertion mark	NA
4.15.1.8	Electrically-driven ride-on toys	NA
4.15.2	Toy bicycles	
4.15.2.2 & 7.15	Toy bicycles – Warnings and instructions for use	NA
4.15.2.3	Toy bicycles – Braking	NA
4.15.3 & 7.16 & 7.19	Rocking horses and similar toys	NA
4.15.4 & 7.16	Toys not propelled by child	NA
4.15.5 & 7.18	Toy scooters	NA
4.16	Heavy immobile toys	NA
4.17.2	All projectiles	NA
4.17.3 & 7.7	Projectile toys with stored energy	NA
4.17.4 & 7.26	Certain projectiles toys without stored energy	NA
4.18 & 7.4	Aquatic toys and inflatable toys	NA

RESULTS:

**MECHANICAL & PHYSICAL PROPERTIES
(EN 71: PART 1 – 2014+A1 – 2018)**

Subclause	Requirement	Result
4.19 & 7.13 & 7.14	Percussion caps	NA
4.20.2.1- 4.20.2.8, 4.20.2.10, 4.20.2.12	Acoustics	NA
4.20.2.9, 4.20.2.11 & 7.14	Acoustics – percussion toys & cap-firing toys	NA
4.21	Toys containing a non-electrical heat source	NA
4.22 & 7.2	Small balls	NA
4.23	Magnet	
4.23.2 a, b & c	Toy other than magnetic / electrical experimental sets intended for children over 8 years	NA
4.23.3 & 7.20	Magnetic / electrical experimental sets intended for children over 8 years	NA
4.24	Yo-yo ball	NA
4.25	Toys attached to food	NA
4.26	Toy Disguise Costumes	NA
4.27.1	Flying toys – General	NA
4.27.2 & 7.25.1	Rotors and propellers on flying toys	NA
4.27.3 & 7.25.2	Rotors and propellers on remote controlled flying toys	NA
FOR TOYS INTENDED FOR CHILDREN UNDER 36 MONTHS		
5.1	General	NA
5.1a	Small parts – as received	NA
5.1b	Small parts, sharp points, sharp edges – after tests	NA
5.1c	Cross section <2mm metal points & wires	NA
5.1e	Toys contain glue	NA
5.1f	Casing of toys	NA
5.2	Fillings, coverings and seams	NA
5.3	Adhesion of plastic sheeting	NA
5.4.2	Cords and chains in toys intended for children under 18 months	NA
5.4.3 & 7.22	Cords and chains in toys intended for children of 18 months or over but under 36 months	NA
5.4.4	Fixed loops, tangled loops and nooses	NA
5.4.5	Cords and chains on pull along toys	NA
5.4.6 & 7.21	Electrical cables	NA
5.4.7	Cross-sectional dimension of certain cords	NA
5.4.8	Self-retracting cords	NA
5.4.9 & 7.11 & 7.23	Toys attached to or intended to be strung across a cradle, cot or perambulator	NA
5.5 & 7.12	Liquid filled toys	NA
5.6	Electrically driven toys	NA
5.7	Glass and porcelain	NA



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 12 of 81

RESULTS:

**MECHANICAL & PHYSICAL PROPERTIES
(EN 71: PART 1 – 2014+A1 – 2018)**

Subclause	Requirement	Result
5.8	Shape and size	NA
5.9 & 7.17	Monofilament fibres	NA
5.10	Small balls	NA
5.11	Play figures	NA
5.12	Hemispheric shaped toys	NA
5.13	Suction cups	NA
5.14	Straps intended to be worn fully or partially around the neck	NA
5.15 & 7.24	Sledges with cords for pulling	NA
6	Packaging	M
WARNINGS, INSTRUCTIONS FOR USE		
7.1	General	M
7.2	Toys not intended for children under 36 months	M
7.5	Functional toys	NA

2009/48/EC GENERAL LABELING REQUIREMENT

Requirement	Result
CE Mark	M
Manufacturer/ Importer name and address	M
Product Identification	M

M = Meet NM = Not Meet N/A = Not Applicable R = Refer to Comment Section



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 13 of 81

RESULTS:

FLAMMABILITY (EN 71 PART 2: 2011 + A1: 2014)

Subclause	Requirement	Result
4.1	Cellulose nitrate	NP
4.1	Surface flash on a piled surface	NA
4.1	Flammable gases	NA
4.1	Extremely flammable liquids, highly flammable liquids, flammable liquids and flammable gels	NA
4.2	Toys to be worn on the head	NA
4.3	Toy disguise costumes and toys intended to be worn by child in play	NA
4.3	warning on product and packaging (10 - 30 mm/s)	NA
4.4	Toys intended to be entered by a child	NA
4.4	warning on product and packaging (10 – 30 mm/s)	NA
4.5	Soft-filled toys	NA

REQUIREMENTS & TEST METHODS CROSS REFERENCE TABLE FOR PART 2

Sub-clause	Test Method	Sub-clause	Test Method	Sub-clause	Test Method	Sub-clause	Test Method
4.2.2	5.2	4.2.4	5.3	4.3	5.4	4.5	5.5
4.2.3	5.3	4.2.5	5.4	4.4	5.4	-	-



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 14 of 81

RESULTS:

APPROPRIATE AGE GRADE DETERMINATION

The Appropriate Age Grade is determined with reference to the Age-grading guidelines of the Annex A of the AS/NZS Standard, "Safety of toys", AS/NZS 8124: Part 1: 2019

Note : The most stringent age grade from the Labeled Age Grade and the Appropriate Age Grade will be used for testing.

Note : If the client does not specify an age grade for testing or request Bureau Veritas Consumer Products Services, Inc. to determine an appropriate age grade, the labeled age grade will be used for testing.

RESULTS:

MECHANICAL & PHYSICAL PROPERTIES – (AS/NZS ISO 8124.1:2019)

Subclause	Requirement	Result
4.1	Normal use	M
4.2	Reasonably foreseeable abuse	M
4.3	Material	M
4.4	Small parts	NA
4.5	Shape, size and strength of certain toys	NA
4.6	Edges	M
4.7	Points	M
4.8	Projections	M
4.9	Metal wires and rods	NA
4.10	Plastic film or plastic bags in packaging and in toys	M
4.11	Cords	NA
4.12	Folding mechanisms	NA
4.13	Holes, clearances and accessibility of mechanisms	M
4.14	Springs	NA
4.15	Stability and overload requirements	NA
4.16	Enclosures	NA
4.17	Simulated protective equipment	NA
4.18	Projectile toys	NA
4.19	Rotors and propellers	NA
4.20	Aquatic toys	NA
4.21	Braking	NA
4.22	Toy bicycles	NA
4.23	Speed limitation of electrically driven ride-on toys	NA
4.24	Toys containing a heat source	NA
4.25	Liquid-filled toys	NA
4.26	Mouth-actuated toys	NA
4.27	Toy roller skates, toy inline skates and toy skateboards	NA
4.28	Percussion caps specifically designed for use in toys	NA
4.29	Acoustic requirement	NA
4.30	Toy scooters	NA
4.31	Magnets and magnetic components	NA
4.32	Yo-yo balls	NA
4.33	Straps intended to be worn fully or partially around the neck	NA
4.34	Sledges and toboggans with cords for pulling	NA
4.35	Jaw entrapment in handles and steering wheels	NA

M = Meet NM = Not Meet N/A = Not Applicable R = Refer to Comment Section



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 16 of 81

RESULTS:

FLAMMABILITY (AS/NZS 8124.2: 2016)

Subclause	Requirement	Result
4.1	Celluloid (cellulose nitrate)	NP
4.1	Surface flash on a piled surface	NA
4.1	Flammable Gases	NA
4.1	Extremely flammable liquids, highly flammable liquids, flammable liquids and flammable gels	NA
4.2	Toys to be worn on the head	NA
4.3	Toy disguise costumes and toys intended to be worn by a child in play	NA
4.3	warning on product and packaging (10 - 30 mm/s)	NA
4.4	Toys intended to be entered by a child	NA
4.4	warning on product and packaging (10 - 30 mm/s)	NA
4.5	Soft - filled toys	NA

M = Meet NM = Not Meet N/A = Not Applicable R = Refer to Comment Section P = Present NP = Not Present



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 17 of 81

RESULTS:

APPROPRIATE AGE GRADE DETERMINATION

The Appropriate Age Grade is recommended with reference to the Toys: Age Classification Guidelines (1998-01-13) of the Product Safety Bureau, Health Canada.

Note : The most stringent age grade from the Labeled Age Grade and the Appropriate Age Grade will be used for testing.

Note : If the client does not specify an age grade for testing or request Bureau Veritas Consumer Products Services, Inc. to determine an appropriate age grade, the labeled age grade will be used for testing.

CANADA CONSUMER PRODUCT SAFETY ACT, TOYS REGULATIONS, SOR/2011-17

Section	Parameter / Requirement	Result
Mechanical Hazards		
4	Flexible film bag used for package	NA
7	Small Toys and Detachable component	NA
8	Metal edge	M
9	Wires frames	NA
10	Plastic Edges	M
11	Wood	M
12	Glass	NA
13	Nails and fasteners	M
14	Safety stops/Locking Device for Folding product	NA
15 (a, b)	Moving Mechanism	NA
15 (c)	Non- Detachable Winding Key Clearance	NA
15 (d)	Detachable Key	NA
16	Projectile Toy	NA
17	Enclosures	NA
18	Stability	NA
19	Auditory hazards	NA
Specific Products - Dolls, Plush Toys and Soft Toys		
28	Exposed Sharp Points and Edges	M
29. (a)	Stuffing Materials shall be clean and free from vermin	NA
29. (b)	Stuffing Materials shall be free from hard and sharp foreign matter	NA
30	Squeaker, Reed and Valve	NA
31	Eyes and Nose	NA



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 18 of 81

RESULTS:

CANADA CONSUMER PRODUCT SAFETY ACT, TOYS REGULATIONS, SOR/2011-17

Section	Parameter / Requirement	Result
Specific Products		
35* & 36*	Plant seeds	NA
37	Pull and Push toys	NA
38*	Toys Steam engine Boilers	NA
39*	Finger Paints	NA
40(a)	Rattles – Sharp wire	NA
40(b, c)	Rattles – Impaction	NA
41	Elastic	NA
42	Yo-Yo type balls	NA
43	Magnetic force	NA
44	Educational experimental kit - Labeling	NA

CANADA CONSUMER PRODUCT SAFETY ACT, SCHEDULE 2

Section	Parameter / Requirement	Result
Mechanical Hazards		
1*	Jequirity Beans	M
8*	Kites	NA
9	Kite strings	NA
14*	Lawn, darts with elongated tips	NA

*M = Meet NM = Not Meet NA = Not Applicable R = Refer to Comment Section * = Non-accredited section*

FLAMMABILITY OF CELLULOSE NITRATE TOY REGULATIONS SOR/2011-17 SECTION 21

Requirement Reference	Observation	Flammability Classification
Section 21	No Flash Effect	M

M = Meet NM-See comment = Not Meet - Refer to Comment Section NA = Not Applicable



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 19 of 81

RESULTS:

CANADA CONSUMER PRODUCT SAFETY ACT – TOYS Regulations SOR/2011-17 FLAMMABILITY OF OUTER COVERING

Test Method	:	CANADA CONSUMER PRODUCT SAFETY ACT – TOYS Regulations SOR/2011-17 FLAMMABILITY OF OUTER COVERING ON DOLL, PLUSH TOY AND SOFT TOY
-------------	---	--

Section	Parameter / Requirement	Result
32	Did Not Ignited	M

M = Meet NM = Not Meet NA = Not Applicable R = Refer to Comment Section



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 20 of 81

RESULTS:

AROMATIC AMINES (AZOCOLLOURANTS) CONTENT (European Regulation (EC) No. 1907/2006 REACH, Annex XVII, Item no. 43, Points 1 and 2)

Test Method: Quantification by Gas Chromatography/Mass Spectrometry (GC/MS)
Additional chromatographic technique employed to confirm positive result by HPLC/TLC

Sample ID	Color / Component	Location	Style
A.	Composite of		
	Deep red fabric	Fabric	C
	Soft orange fabric	Fabric	C
	Deep green fabric	Fabric	C
B.	Dull yellow fabric	Fabric	C
	Sky blue fabric	Pocket	C
	Flat orange fabric	Fabric	E
C.	Deep blue cord	Tie	C
	Lemon yellow cord	Tie	E
D.	Dull blue felt	Pocket	C
	Matt red felt	Felt	C,E
	Matt yellow felt	Felt	C,E
E.	Matt green felt	Felt	C
	Matt orange felt	Felt	C
F.	Matt blue felt	Felt	E
	Deep orange felt	Felt	E
G.	Multicolor printed matt white felt	Felt	E



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 21 of 81

RESULTS:

AROMATIC AMINES (AZOCOLLOURANTS) CONTENT (European Regulation (EC) No. 1907/2006 REACH, Annex XVII, Item no. 43, Points 1 and 2)

Test Method: Quantification by Gas Chromatography/Mass Spectrometry (GC/MS)
Additional chromatographic technique employed to confirm positive result by HPLC/TLC

Test Parameter:		Aromatic Amines (Azocolourants)		
Requirement:		30 mg/kg		
Sample ID	Test Method	Detected Amine Number	Concentration (mg/kg (ppm))	Conclusion
A.	II	-	LT 10	PASS
B.	II	-	LT 10	PASS
C.	II	-	LT 10	PASS
D.	II	-	LT 10	PASS
E.	I	-	LT 10	PASS
F.	I	-	LT 10	PASS
G.	I+II	-	LT 10	PASS

ND = Not Detected (Detection Limit = 10 mg/kg (ppm))

mg/kg = milligrams per kilogram

ppm = parts per million

NR = Not Requested

* = The specimen is a minor component. As only a reduced mass (< 0.5 g) could be used for the test the result may have a greater uncertainty due to lower material homogeneity

Amine No. = Refer to List of Banned Amines for the description of the detected Amine.

Test Method I = European Standard EN 14362-1: 2017, Clauses 9, 10.2 and afterwards.

Test Method II = European Standard EN 14362-1: 2017, Clauses 9, 10.1, 10.3 and afterwards.

Test Method III = International Standard ISO 17234-1: 2015.

Remark:

The list of aromatic amines in azo colorants is summarized in table of Appendix.

The CAS-number 97-56-3 (no. 5) and 99-55-8 (no. 6) are further reduced to CAS-number 95-53-4 (no. 18) and 95-80-7 (no. 19), respectively.

The colorant(s) of Test Item(s), that are able to form 4-aminoazobenzene, is (are) able to generate aniline and 1,4-phenylenediamine under the condition of Test Method.

The absence of 4-aminoazobenzene is inferred by the absence of aniline and 1,4-phenylenediamine under the condition of Test Method.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 22 of 81

RESULTS:

AROMATIC AMINES (AZOCOLLOURANTS) CONTENT (European Regulation (EC) No. 1907/2006 REACH, Annex XVII, Item no. 43, Points 1 and 2)

Test Method: Quantification by Gas Chromatography/Mass Spectrometry (GC/MS)
Additional chromatographic technique employed to confirm positive result by HPLC/TLC

LIST OF BANNED AMINES Specified Amines		
Number	Chemical Name	CAS Number
1.	4-aminobiphenyl	92-67-1
2.	Benzidine	92-87-5
3.	4-chloro-o-toluidine	95-69-2
4.	2-naphthylamine	91-59-8
5.	o-aminoazotoluene	97-56-3
6.	5-nitro-o-toluidine	99-55-8
7.	4-chloroaniline	106-47-8
8.	4-methoxy-m-phenylenediamine	615-05-4
9.	4,4'-diaminodiphenylmethane	101-77-9
10.	3,3'-dichlorobenzidine	91-94-1
11.	3,3'-dimethoxybenzidine	119-90-4
12.	3,3'-dimethylbenzidine	119-93-7
13.	4,4'-methylenedi-o-toluidine	838-88-0
14.	p-cresidine	120-71-8
15.	4,4'-methylene-bis-(2-chloro-aniline)	101-14-4
16.	4,4'-oxydianiline	101-80-4
17.	4,4'-thiodianiline	139-65-1
18.	o-toluidine	95-53-4
19.	4-methyl-m-phenylenediamine	95-80-7
20.	2,4,5-trimethylaniline	137-17-7
21.	o-anisidine	90-04-0
22.	4-amino azobenzene	60-09-3



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 23 of 81

RESULTS:

TOTAL LEAD CONTENT IN SURFACE COATING BY COMPOSITE TESTING ("Ban of Lead-containing paint and certain consumer products bearing Lead-containing paint", Consumer Product Safety Improvement Act (CPSIA) of 2008)

Test Method: U.S. CPSC-CH-E1003.09.1:2011

Element:				Lead		
Requirement: Maximum allowable limit:				90 mg/kg		
Sample Description				Result (mg/kg)		Conclusion
Color / Component		Location	Style	Overall	Potential	
(A)	Deep yellow coating Reddish brown / clear coating	Block Base	B B	LT 10	-	PASS
(B)	All coating / white coating	Board & dice	B,D	LT 10	-	PASS
(C)	All coating	Book	F	LT 10	-	PASS
(D)	Purple coating Brown coating	Block Shape board	F F	LT 10	-	PASS
(E)	Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E	11	-	PASS
(F)	Bright red coating	Bright red paint (A1Y)	A-F	LT 10	-	PASS
(G)	Orange coating	Orange paint (A2Y)	F	LT 10	-	PASS
(H)	Light yellow coating	Light yellow paint (A3Y)	B,F	LT 10	-	PASS
(I)	Dark green coating	Dark green paint (A5Y)	A-E	LT 10	-	PASS
(J)	Light green coating	Light green paint (A6Y)	F	LT 10	-	PASS
(K)	Dark blue coating	Dark blue paint (A7Y)	A,F	LT 10	-	PASS
(L)	Light blue coating	Light blue paint (A8Y)	F	LT 10	-	PASS
(M)	Dark brown coating	Dark brown paint (A10Y)	F	LT 10	-	PASS
(N)	White coating	White paint (A16Y)	D	LT 10	-	PASS
(O)	Clear lacquer	Clear lacquer paint (A21Y)	A-F	LT 10	-	PASS

LT = Less Than

* = Average of duplicate analyses

mg/kg = milligrams per kilogram (ppm = parts per million)

Potential = Estimated lead content per component is based on calculation by component individual weight



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 24 of 81

RESULTS:

TOTAL LEAD CONTENT IN SUBSTRATE BY COMPOSITE TESTING (100PPM) (Consumer Product Safety Improvement Act (CPSIA) of 2008)

Test Method: U.S. CPSC-CH-E1001-08.3:2012 or U.S. CPSC-CH-E1002-08.3:2012

Analyte	Lead	
Requirement: Maximum allowable limit:	100 mg/kg	

Analyte				Lead (Pb)	Conclusion
Sample Description				Result (mg/kg)	
	Color / Component	Location	Style		
(A)	Shiny silver printed clear plastic Flesh plastic Clear laminated multicolor printed white paper board	Mirror Plastic screw Paper Board	A A B	LT 10	PASS
(B)	Clear plastic Translucent plastic Flat white plastic	End of tie Zipper teeth Fastener	C,E C,E C,E	LT 10	PASS
(C)	Clear red plastic Clear yellow plastic Clear blue plastic	Block Block Block	F F F	LT 10	PASS
(D)	Clear green plastic Matt white plastic Bright clear plastic	Block Shape board & book Spiral of book	F F F	LT 10	PASS
(E)	Silvery metal	Screw	A-C,E	LT 10	PASS
(F)	Dull silvery metal	Big hexgon screw	A	LT 10	PASS
(G)	Soft silvery metal	Loop of tie	C,E	LT 10	PASS
(H)	Matt silvery metal	Zipper tag	C,E	12	PASS
(I)	Flat silvery metal	Zipper slide	C,E	26	PASS
(J)	Light silvery metal	Upper female fastener	E	LT 10	PASS
(K)	Deep silvery metal	Lower female fastener	E	LT 10	PASS
(L)	Dark silvery metal	Spring of fastener	E	LT 10	PASS
(M)	Sharp silvery metal	Upper male fastener	E	LT 10	PASS
(N)	Bright silvery metal	Lower male fastener	E	LT 10	PASS
(O)	Light flesh /flesh wood	Wooden board	B-D	LT 10	PASS
(P)	Bright light flesh /bright flesh wood	Wooden board	A,E,F	LT 10	PASS

LT = Less Than

* = Average of duplicate analyses

mg/kg = milligrams per kilogram (ppm = parts per million)



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 25 of 81

RESULTS:

HEAVY METALS CONTENT IN SURFACE COATING (Canada Consumer Product Safety Act - Toys Regulations, SOR/2011-17 Sec. 23 with Amendment in SOR/2016-195)

Sample Identity	Color	Location	Style
A.	Deep yellow coating Reddish brown / clear coating	Block Base	B B
B.	All coating / white coating	Board & dice	B,D
C.	All coating	Book	F
D.	Purple coating Brown coating	Block Shape board	F F
E.	Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E
F.	Bright red coating	Bright red paint (A1Y)	A-F
G.	Orange coating	Orange paint (A2Y)	F
H.	Light yellow coating	Light yellow paint (A3Y)	B,F
I.	Dark green coating	Dark green paint (A5Y)	A-E
J.	Light green coating	Light green paint (A6Y)	F
K.	Dark blue coating	Dark blue paint (A7Y)	A,F
L.	Light blue coating	Light blue paint (A8Y)	F
M.	Dark brown coating	Dark brown paint (A10Y)	F
N.	White coating	White paint (A16Y)	D
O.	Clear lacquer	Clear lacquer paint (A21Y)	A-F

Analyte		As	Ba	Cd	Hg	Pb	Sb	Se	
	Method	Result (mg/kg)							Conclusion
(A)	(T)	LT 10	57	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(B)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(C)	(T)	LT 10	11	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(D)	(T)	LT 10	10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(E)	(T)	LT 10	29	LT 10	ND	11	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(F)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(G)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(H)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(I)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(J)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(K)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 27 of 81

RESULTS:

HEAVY METALS CONTENT IN SURFACE COATING (Canada Consumer Product Safety Act - Toys Regulations, SOR/2011-17 Sec. 23 with Amendment in SOR/2016-195)

Analyte		As	Ba	Cd	Hg	Pb	Sb	Se	
Maximum	(T)	-	-	-	ND	90	-	-	
Limit (mg/kg)	(S)	1000	1000	1000	-	-	1000	1000	

Analyte		As	Ba	Cd	Hg	Pb	Sb	Se	
	Method	Result (mg/kg)							Conclusion
(L)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(M)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(N)	(T)	LT 10	LT 10	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	
(O)	(T)	LT 10	12	LT 10	ND	LT 10	LT 10	LT 10	PASS
	(S)	-	-	-	-	-	-	-	

mg/kg = milligrams per kilogram (ppm=parts per million)

*= Average of duplicate analysis

ND = Not detected (Detection Limit = 10 mg/kg)

(T) = Total Analysis (With referenced to ASTM F963-17 Sec. 8.3)

(S) = Soluble analysis (Canada Product Safety Manual Book 5, Part-B, C-03 (2014))

LT = Less Than

As = Arsenic, Ba = Barium, Cd = Cadmium,

Hg = Mercury, Pb = Lead, Sb = Antimony,

Se = Selenium



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 28 of 81

RESULTS:

TOTAL LEAD CONTENT (Canada Consumer Product Safety Act – Consumer Products Containing Lead Regulations SOR/2018-83)

Test Method: Health Canada, Product Safety Laboratory, Reference Manual, Book 5 - Laboratory Policies and Procedures – Part B: Test Method Section, Method C-02.2:2017, C-02.3:2017 or C-02.4:2017

Analyte	Lead	
Requirement: Maximum allowable limit:	90 mg/kg	

Analyte				Lead (Pb)	Conclusion
Sample Description				Result (mg/kg)	
	Color / Component	Location	Style		
(A)	Deep yellow coating Reddish brown / clear coating	Block Base	B B	LT 10	PASS
(B)	All coating / white coating	Board & dice	B,D	LT 10	PASS
(C)	All coating	Book	F	LT 10	PASS
(D)	Purple coating Brown coating	Block Shape board	F F	LT 10	PASS
(E)	Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E	11	PASS
(F)	Shiny silver printed clear plastic Flesh plastic Clear laminated multicolor printed white paper board	Mirror Plastic screw Paper Board	A A B	LT 10	PASS
(G)	Clear plastic Translucent plastic Flat white plastic	End of tie Zipper teeth Fastener	C,E C,E C,E	LT 10	PASS
(H)	Clear red plastic Clear yellow plastic Clear blue plastic	Block Block Block	F F F	LT 10	PASS
(I)	Clear green plastic Matt white plastic Bright clear plastic	Block Shape board & book Spiral of book	F F F	LT 10	PASS
(J)	Silvery metal	Screw	A-C,E	LT 10	PASS
(K)	Dull silvery metal	Big hexgon screw	A	LT 10	PASS
(L)	Soft silvery metal	Loop of tie	C,E	LT 10	PASS
(M)	Matt silvery metal	Zipper tag	C,E	12	PASS
(N)	Flat silvery metal	Zipper slide	C,E	26	PASS
(O)	Light silvery metal	Upper female fastener	E	LT 10	PASS
(P)	Deep silvery metal	Lower female fastener	E	LT 10	PASS
(Q)	Dark silvery metal	Spring of fastener	E	LT 10	PASS
(R)	Sharp silvery metal	Upper male fastener	E	LT 10	PASS
(S)	Bright silvery metal	Lower male fastener	E	LT 10	PASS



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 29 of 81

RESULTS:

TOTAL LEAD CONTENT (Canada Consumer Product Safety Act – Consumer Products Containing Lead Regulations SOR/2018-83)

Test Method: Health Canada, Product Safety Laboratory, Reference Manual, Book 5 - Laboratory Policies and Procedures – Part B: Test Method Section, Method C-02.2:2017, C-02.3:2017 or C-02.4:2017

Analyte	Lead	
Requirement: Maximum allowable limit:	90 mg/kg	

Analyte				Lead (Pb)	Conclusion
Sample Description				Result	
Color / Component	Location	Style		(mg/kg)	
(T) Bright red coating	Bright red paint (A1Y)	A-F		LT 10	PASS
(U) Orange coating	Orange paint (A2Y)	F		LT 10	PASS
(V) Light yellow coating	Light yellow paint (A3Y)	B,F		LT 10	PASS
(W) Dark green coating	Dark green paint (A5Y)	A-E		LT 10	PASS
(X) Light green coating	Light green paint (A6Y)	F		LT 10	PASS
(Y) Dark blue coating	Dark blue paint (A7Y)	A,F		LT 10	PASS
(Z) Light blue coating	Light blue paint (A8Y)	F		LT 10	PASS
(AA) Dark brown coating	Dark brown paint (A10Y)	F		LT 10	PASS
(AB) White coating	White paint (A16Y)	D		LT 10	PASS
(AC) Clear lacquer	Clear lacquer paint (A21Y)	A-F		LT 10	PASS
(AD) Light flesh /flesh wood	Wooden board	B-D		LT 10	PASS
(AE) Bright light flesh /bright flesh wood	Wooden board	A,E,F		LT 10	PASS

LT = Less Than

* = Average of duplicate analyses

mg/kg =milligrams per kilogram (ppm=parts per million)

ND=Not detected



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 30 of 81

RESULTS:

CADMIUM CONTENT (European Regulation (EC) No. 1907/2006 REACH Annex XVII, Item no. 23)

Category:				Plastics			
Element:				Cadmium			
Test Method				BS EN 1122: 2001, Method B			
Maximum Allowable Limit:				100 mg/kg (0.01% by weight)			
Sample Description				Reading 1	Reading 2	Average	Conclusion
Color / Component	Location	Style	Result (mg/kg)				
(A)	Shiny silver printed clear plastic	Mirror	A	LT 10	LT 10	LT 10	Pass
	Flesh plastic	Plastic screw	A				
	Clear laminated multicolor printed white paper board	Paper Board	B				
	Clear plastic	End of tie	C,E				
(B)	Translucent plastic	Zipper teeth	C,E	LT 10	LT 10	LT 10	Pass
	Flat white plastic	Fastener	C,E				
	Clear red plastic	Block	F				
	Clear yellow plastic	Block	F				
(C)	Clear blue plastic	Block	F	LT 10	LT 10	LT 10	Pass
	Clear green plastic	Block	F				
	Matt white plastic	Shape board & book	F				
	Bright clear plastic	Spiral of book	F				

LT = Less than

= Insufficient sample for duplicate analyses

mg/kg = milligrams per kilogram (ppm = parts per million)

Operator: Zhang Shao Zheng, Ryan



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 31 of 81

RESULTS:

CADMIUM CONTENT (European Regulation (EC) No. 1907/2006 REACH Annex XVII, Item no. 23)

Category:			Paints on Painted Article	
Element:			Cadmium	
Test Method:			In house acid digestion	
Maximum Allowable Limit:			1000 mg/kg (0.1% by weight)	
Test Component			Result (mg/kg)	Conclusion
Colour/Component	Location	Style		
(A) Deep yellow coating Reddish brown / clear coating	Block Base	B B	LT 10	Pass
(B) All coating / white coating	Board & dice	B,D	LT 10	Pass
(C) All coating	Book	F	LT 10	Pass
(D) Purple coating Brown coating	Block Shape board	F F	LT 10	Pass
(E) Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E	LT 10	Pass
(F) Bright red coating	Bright red paint (A1Y)	A-F	LT 10	Pass
(G) Orange coating	Orange paint (A2Y)	F	LT 10	Pass
(H) Light yellow coating	Light yellow paint (A3Y)	B,F	LT 10	Pass
(I) Dark green coating	Dark green paint (A5Y)	A-E	LT 10	Pass
(J) Light green coating	Light green paint (A6Y)	F	LT 10	Pass
(K) Dark blue coating	Dark blue paint (A7Y)	A,F	LT 10	Pass
(L) Light blue coating	Light blue paint (A8Y)	F	LT 10	Pass
(M) Dark brown coating	Dark brown paint (A10Y)	F	LT 10	Pass
(N) White coating	White paint (A16Y)	D	LT 10	Pass
(O) Clear lacquer	Clear lacquer paint (A21Y)	A-F	LT 10	Pass

LT = Less than

* = Average of duplicate analyses

mg/kg = milligrams per kilogram (ppm = parts per million)



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 32 of 81

RESULTS:

APPROPRIATE AGE GRADE DETERMINATION

The Appropriate Age Grade is determined with reference to the EN71: Part 1 : 2014 +A1:2018, CEN ISO/TR 8124-8:2016 Safety of toys - Part 8: Age Determination Guidelines prepared by Technical Committee CEN/TC 52 and Age Grade Determination Guidelines of the Consumer Product Safety Commission (CPSC).

Note : The most stringent age grade from the Labeled Age Grade and the Appropriate Age Grade will be used for testing.

Note : If the client does not specify an age grade for testing or request Bureau Veritas Consumer Products Services, Inc. to determine an appropriate age grade, the labeled age grade will be used for testing.

FORMALDEHYDE RELEASE IN ACCESSIBLE RESIN-BONDED WOOD COMPONENTS (EN 71: Part 9: 2005 and Amendment A1: 2007)

Test Method: BS EN 717 Part 3, Wood-based panels - Determination of formaldehyde release - Part 3: Formaldehyde release by the flask method.

Parameter:					Formaldehyde Release	
Maximum allowable limit:					80 (mg/kg (ppm))	
Test Component				Moisture Content (%)	Result (mg/kg (ppm))	Conclusion
	Color/Component	Location	Style No.			
A.	Light flesh /flesh wood	Wooden board	B-D		LT 16	Pass
B.	Bright light flesh /bright flesh wood	Wooden board	A,E,F		LT 16	Pass

LT = Less than

mg/kg (ppm) = milligrams per kilogram (ppm = parts per million)



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 33 of 81

RESULTS:

SOLUBLE HEAVY METALS CONTENT IN SURFACE COATING (ASTM F963-17, Section 4.3.5.1(2))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.2 to 8.3.4

Sample Identity	Color	Location	Style
A.	Deep yellow coating	Block	B
B.	Reddish brown / clear coating	Base	B
C.	All coating / white coating	Board & dice	B,D
D.	All coating	Book	F
E.	Purple coating	Block	F
F.	Brown coating	Shape board	F
G.	Bright red coating	Bright red paint (A1Y)	A-F
H.	Orange coating	Orange paint (A2Y)	F
I.	Light yellow coating	Light yellow paint (A3Y)	B,F
J.	Dark green coating	Dark green paint (A5Y)	A-E
K.	Light green coating	Light green paint (A6Y)	F
L.	Dark blue coating	Dark blue paint (A7Y)	A,F
M.	Light blue coating	Light blue paint (A8Y)	F
N.	Dark brown coating	Dark brown paint (A10Y)	F
O.	White coating	White paint (A16Y)	D
P.	Clear lacquer	Clear lacquer paint (A21Y)	A-F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 34 of 81

RESULTS:

SOLUBLE HEAVY METALS CONTENT IN SURFACE COATING (ASTM F963-17, Section 4.3.5.1(2))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.2 to 8.3.4

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	
Maximum Limit (mg/kg)	25	1000	75	60	60	90	60	500	
Analytical Correction	60%	30%	30%	30%	50%	30%	60%	60%	

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	Mass of Trace Amount	Conclusion
Sample	Result (mg/kg)								(g)	
A.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
B.	LT 2	3	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
C.	LT 2	3	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
D.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
E.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
F.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
G.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0856	PASS
H.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0612	PASS
I.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0691	PASS
J.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0666	PASS
K.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0738	PASS
L.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0580	PASS
M.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0781	PASS
N.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0543	PASS
O.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0712	PASS
P.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	0.0806	PASS

LT = Less Than

CR = adjusted analytical result

mg/kg = milligrams per kilogram (ppm=parts per million)

* = Average of duplicate analysis

As = Arsenic, Ba = Barium, Cd = Cadmium,

Cr = Chromium, Hg = Mercury, Pb = Lead,

Sb = Antimony, Se = Selenium



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 35 of 81

RESULTS:

SOLUBLE HEAVY METALS CONTENT IN SUBSTRATE (ASTM F963-17, Section 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.5 (Excluding 8.3.5.5(3))

Sample Identity	Color	Location	Style
Type I: Substrate other than modeling clay			
A	Shiny silver printed clear plastic	Mirror	A
B	Flesh plastic	Plastic screw	A
C	Clear laminated multicolor printed white paper board	Paper Board	B
D	Clear plastic	End of tie	C,E
E	Translucent plastic	Zipper teeth	C,E
F	Flat white plastic	Fastener	C,E
G	Clear red plastic	Block	F
H	Clear yellow plastic	Block	F
I	Clear blue plastic	Block	F
J	Clear green plastic	Block	F
K	Matt white plastic	Shape board & book	F
L	Bright clear plastic	Spiral of book	F
M	Deep red fabric / red thread	Fabric	C
N	Soft orange fabric / orange thread	Fabric	C
O	Deep green fabric / green thread	Fabric	C
P	Dull yellow fabric / yellow thread	Fabric	C
Q	Sky blue fabric / blue thread	Pocket	C
R	Dull blue felt	Pocket	C
S	Soft white hook & loop fastener	Velcro	C,E
T	Bright white fabric / white thread	Zipper band	C,E
U	Matt red felt	Felt	C,E
V	Matt yellow felt	Felt	C,E
W	Matt green felt	Felt	C
X	Matt orange felt	Felt	C
Y	Deep blue cord	Tie	C
Z	Lemon yellow cord	Tie	E



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 36 of 81

RESULTS:

SOLUBLE HEAVY METALS CONTENT IN SUBSTRATE (ASTM F963-17, Section 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.5 (Excluding 8.3.5.5(3))

Sample Identity	Color	Location	Style
AA.	Matt blue felt	Felt	E
AB.	Deep orange felt	Felt	E
AC.	Flat orange fabric	Fabric	E
AD.	Multicolor printed matt white felt	Felt	E
AE.	Beige felt	Base	C,E
AF.	Light brown wood	Wooden board	B,D,F
AG.	Light flesh /flesh wood	Wooden board	B-D
AH.	Bright light flesh /bright flesh wood	Wooden board	A,E,F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 38 of 81

RESULTS:

SOLUBLE HEAVY METALS CONTENT IN SUBSTRATE (ASTM F963-17, Section 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.5 (Excluding 8.3.5.5(3))

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	
Max. Limit Type I (mg/kg)	25	1000	75	60	60	90	60	500	
Max. Limit Type II (mg/kg)	25	250	50	25	25	90	60	500	
Analytical Correction	60%	30%	30%	30%	50%	30%	60%	60%	

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	Mass of Trace Amount (g)	Conclusion
Sample	Result (mg/kg)									
P	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	6	LT 2		PASS
Q	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
R	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	3	LT 2		PASS
S	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
T	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
U	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	4	LT 2		PASS
V	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	15	LT 2		PASS
W	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
X	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	4	LT 2		PASS
Y	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
Z	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AA.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	3	LT 2		PASS
AB.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	10	LT 2		PASS
AC.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	11	LT 2		PASS
AD.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	34	LT 2		PASS



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 39 of 81

RESULTS:

SOLUBLE HEAVY METALS CONTENT IN SUBSTRATE (ASTM F963-17, Section 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.5 (Excluding 8.3.5.5(3))

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	
Max. Limit Type I (mg/kg)	25	1000	75	60	60	90	60	500	
Max. Limit Type II (mg/kg)	25	250	50	25	25	90	60	500	
Analytical Correction	60%	30%	30%	30%	50%	30%	60%	60%	

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	Mass of Trace Amount (g)	Conclusion
Sample	Result (mg/kg)									
AE.	LT 2	2	LT 2	LT 2	LT 2	LT 2	12	LT 2		PASS
AF.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AG.	LT 2	3	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AH.	LT 2	10	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS

mg/kg = milligrams per kilogram (ppm=parts per million)

CR = adjusted analytical result

LT = Less Than

ND = None Detected

As = Arsenic, Ba = Barium, Cd = Cadmium,

Cr = Chromium, Hg = Mercury, Pb = Lead,

Sb = Antimony, Se = Selenium

Detection limit (mg/kg): Each element 2

Remark:

Textiles (natural or synthetic) are exempted for lead content requirement according to clarification of Toy Industry Association for ASTM F963-17. The lead content analysis result of corresponding material herein is for client's reference only.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 40 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (AS/NZS 8124 Part 3: 2012 with Amendment No. 1: 2016)

Test Method: Soluble heavy metals content analysis was determined by Inductively Coupled Plasma Spectrometry.

Sample Identity	Color / Component	Location	Style
Type I: Coatings			
A.	Deep yellow coating	Block	B
B.	Reddish brown / clear coating	Base	B
C.	All coating / white coating	Board & dice	B,D
D.	All coating	Book	F
E.	Purple coating	Block	F
F.	Brown coating	Shape board	F
Type II: Polymeric Materials			
G.	Shiny silver printed clear plastic	Mirror	A
H.	Flesh plastic	Plastic screw	A
I.	Clear laminated multicolor printed white paper board	Paper Board	B
J.	Clear plastic	End of tie	C,E
K.	Translucent plastic	Zipper teeth	C,E
L.	Flat white plastic	Fastener	C,E
M.	Clear red plastic	Block	F
N.	Clear yellow plastic	Block	F
O.	Clear blue plastic	Block	F
P.	Clear green plastic	Block	F
Q.	Matt white plastic	Shape board & book	F
R.	Bright clear plastic	Spiral of book	F
Type IV: Textiles			
S.	Deep red fabric / red thread	Fabric	C
T.	Soft orange fabric / orange thread	Fabric	C
U.	Deep green fabric / green thread	Fabric	C
V.	Dull yellow fabric / yellow thread	Fabric	C
W.	Sky blue fabric / blue thread	Pocket	C
X.	Dull blue felt	Pocket	C
Y.	Soft white hook & loop fastener	Velcro	C,E
Z.	Bright white fabric / white thread	Zipper band	C,E



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 41 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (AS/NZS 8124 Part 3: 2012 with Amendment No. 1: 2016)

Test Method: Soluble heavy metals content analysis was determined by Inductively Coupled Plasma Spectrometry.

Sample Identity	Color / Component	Location	Style
AA.	Matt red felt	Felt	C,E
AB.	Matt yellow felt	Felt	C,E
AC.	Matt green felt	Felt	C
AD.	Matt orange felt	Felt	C
AE.	Deep blue cord	Tie	C
AF.	Lemon yellow cord	Tie	E
AG.	Matt blue felt	Felt	E
AH.	Deep orange felt	Felt	E
AI.	Flat orange fabric	Fabric	E
AJ.	Multicolor printed matt white felt	Felt	E
AK.	Beige felt	Base	C,E
Type I: Coatings			
AL.	Bright red coating	Bright red paint (A1Y)	A-F
AM.	Orange coating	Orange paint (A2Y)	F
AN.	Light yellow coating	Light yellow paint (A3Y)	B,F
AO.	Dark green coating	Dark green paint (A5Y)	A-E
AP.	Light green coating	Light green paint (A6Y)	F
AQ.	Dark blue coating	Dark blue paint (A7Y)	A,F
AR.	Light blue coating	Light blue paint (A8Y)	F
AS.	Dark brown coating	Dark brown paint (A10Y)	F
AT.	White coating	White paint (A16Y)	D
AU.	Clear lacquer	Clear lacquer paint (A21Y)	A-F
Type VI: Other Materials Whether Mass Coloured Or Not			
AV.	Light brown wood	Wooden board	B,D,F
AW.	Light flesh /flesh wood	Wooden board	B-D
AX.	Bright light flesh /bright flesh wood	Wooden board	A,E,F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 43 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (AS/NZS 8124 Part 3: 2012 with Amendment No. 1: 2016)

Test Method: Soluble heavy metals content analysis was determined by Inductively Coupled Plasma Spectrometry.

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	
Max. Limit All except Type VIII (mg/kg)	25	1000	75	60	60	90	60	500	
Max. Limit Type VIII (mg/kg)	25	250	50	25	25	90	60	500	
Analytical Correction	60%	30%	30%	30%	50%	30%	60%	60%	

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	Mass of Trace Amount (g)	Conclusion
Sample	Result (mg/kg)									
R.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
S.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	3	LT 2		PASS
T.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	4	LT 2		PASS
U.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
V.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	6	LT 2		PASS
W.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
X.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	3	LT 2		PASS
Y.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
Z.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AA.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	4	LT 2		PASS
AB.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	15	LT 2		PASS
AC.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AD.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	4	LT 2		PASS
AE.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AF.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AG.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	3	LT 2		PASS
AH.	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2	10	LT 2		PASS



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 45 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (AS/NZS 8124 Part 3: 2012 with Amendment No. 1: 2016)

Test Method: Soluble heavy metals content analysis was determined by Inductively Coupled Plasma Spectrometry.

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	
Max. Limit All except Type VIII (mg/kg)	25	1000	75	60	60	90	60	500	
Max. Limit Type VIII (mg/kg)	25	250	50	25	25	90	60	500	
Analytical Correction	60%	30%	30%	30%	50%	30%	60%	60%	

Analyte	As	Ba	Cd	Cr	Hg	Pb	Sb	Se	Mass of Trace Amount	Conclusion
Sample	Result (mg/kg)								(g)	
AW.	LT 2	3	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS
AX.	LT 2	10	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2		PASS

mg/kg = milligrams per kilogram (ppm=parts per million)

CR = adjusted analytical result

LT = Less Than

* = Average of duplicate analysis

As = Arsenic, Ba = Barium, Cd = Cadmium,

Cr = Chromium, Hg = Mercury, Pb = Lead,

Sb = Antimony, Se = Selenium



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 46 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Sample Identity	Color	Location	Style
A.	Deep yellow coating	Block	B
B.	Reddish brown / clear coating	Base	B
C.	All coating / white coating	Board & dice	B,D
D.	All coating	Book	F
E.	Purple coating	Block	F
F.	Brown coating	Shape board	F
G.	Shiny silver printed clear plastic	Mirror	A
H.	Flesh plastic	Plastic screw	A
I.	Clear laminated multicolor printed white paper board	Paper Board	B
J.	Clear plastic	End of tie	C,E
K.	Translucent plastic	Zipper teeth	C,E
L.	Flat white plastic	Fastener	C,E
M.	Clear red plastic	Block	F
N.	Clear yellow plastic	Block	F
O.	Clear blue plastic	Block	F
P.	Clear green plastic	Block	F
Q.	Matt white plastic	Shape board & book	F
R.	Bright clear plastic	Spiral of book	F
S.	Deep red fabric / red thread	Fabric	C
T.	Soft orange fabric / orange thread	Fabric	C
U.	Deep green fabric / green thread	Fabric	C
V.	Dull yellow fabric / yellow thread	Fabric	C
W.	Sky blue fabric / blue thread	Pocket	C
X.	Dull blue felt	Pocket	C
Y.	Soft white hook & loop fastener	Velcro	C,E
Z.	Bright white fabric / white thread	Zipper band	C,E

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Sample Identity	Color	Location	Style
AA.	Matt red felt	Felt	C,E
AB.	Matt yellow felt	Felt	C,E
AC.	Matt green felt	Felt	C
AD.	Matt orange felt	Felt	C
AE.	Deep blue cord	Tie	C
AF.	Lemon yellow cord	Tie	E
AG.	Matt blue felt	Felt	E
AH.	Deep orange felt	Felt	E
AI.	Flat orange fabric	Fabric	E
AJ.	Multicolor printed matt white felt	Felt	E
AK.	Dark green coating	Pattern & logo	A-E
AL.	Light flesh / flesh wood	Wooden board	B-D
AM.	Bright light flesh / bright flesh wood	Wooden board	A,E,F
AN.	Bright red coating	Bright red paint (A1Y)	A-F
AO.	Orange coating	Orange paint (A2Y)	F
AP.	Light yellow coating	Light yellow paint (A3Y)	B,F
AQ.	Light green coating	Light green paint (A6Y)	F
AR.	Dark blue coating	Dark blue paint (A7Y)	A,F
AS.	Light blue coating	Light blue paint (A8Y)	F
AT.	Dark brown coating	Dark brown paint (A10Y)	F
AU.	White coating	White paint (A16Y)	D
AV.	Clear lacquer	Clear lacquer paint (A21Y)	A-F
AW.	Light brown wood	Wooden board	B,D,F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 48 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		A.	B.	C.	D.	E.	F.
Aluminium (Al)	70000	33	15	44	5	9	5
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	3	3	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.59	0.30	0.29	0.60	0.27	0.36
Chromium VI (Cr VI)	0.2	#LT0.0020	#LT0.0020	#LT0.0020	#LT0.0020	#LT0.0020	#LT0.0020
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	4	2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	4	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	2	LT 2	LT 2
Zinc (Zn)	46000	42	100	42	7	9	5
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 49 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		G.	H.	I.	J.	K.	L.
Aluminium (Al)	70000	8	4	160	3	LT 2	2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	LT 0.050	0.11	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.2			#LT0.0020			
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	7	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	20	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 2	2	LT 2	LT 2	LT 2	3
Mass of trace amount (gram)					0.0804		
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 50 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		M.	N.	O.	P.	Q.	R.
Aluminium (Al)	70000	4	7	4	3	2	LT 2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.060	LT 0.050	LT 0.050	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.2	#LT0.0020					
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	12	2	LT 2	LT 2	LT 2	LT 2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 51 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		S.	T.	U.	V.	W.	X.
Aluminium (Al)	70000	3	2	4	3	7	3
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.053	0.053	0.051	LT 0.050	LT 0.050	0.074
Chromium VI (Cr VI)	0.2						#LT0.0020
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	3	4	LT 2	6	LT 2	3
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 2	3	4	LT 2	LT 2	2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 52 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		Y.	Z.	AA.	AB.	AC.	AD.
Aluminium (Al)	70000	LT 2	2	3	3	LT 2	LT 2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	LT 0.050	0.064	0.052	0.055	LT 0.050
Chromium VI (Cr VI)	0.2			#LT0.0020		#LT0.0020	
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	28	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	4	15	LT 2	4
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 2	LT 2	LT 2	71	2	LT 2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 53 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		AE.	AF.	AG.	AH.	AI.	AJ.
Aluminium (Al)	70000	2	3	4	3	LT 2	2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.078	0.050	LT 0.050	0.052	LT 0.050	0.064
Chromium VI (Cr VI)	0.2	#LT0.0020					#LT0.0020
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	3	10	11	34
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	4	5	LT 2	50	50	2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 54 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
	Category III	AK.	AL.	AM.	AN.	AO.	AP.
Aluminium (Al)	70000	10	LT 2	2	LT 2	LT 2	2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	6	4	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	0.12	LT 0.050	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.2		#LT0.0020				
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	33	4	LT 2	LT 2	LT 2
Nickel (Ni)	930	4	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	2	4	LT 2	LT 2	LT 2
Zinc (Zn)	46000	4	56	21	53	LT 2	140
Mass of trace amount (gram)					0.0856	0.0612	0.0691
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 55 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		AQ.	AR.	AS.	AT.	AU.	AV.
Aluminium (Al)	70000	2	LT 2	LT 2	LT 2	6	LT 2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	6	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	LT 0.050	LT 0.050	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.2						
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	83	97	64	150	96	77
Mass of trace amount (gram)		0.0738	0.0580	0.0781	0.0543	0.0712	0.0806
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 56 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2013+A3:2018)

Test Method : European Standard EN 71 Part 3: 2013+A3:2018, Annex E.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		Category III	AW.	-	-	-	-
Aluminium (Al)	70000	LT 2	-	-	-	-	-
Arsenic (As)	47	LT 2	-	-	-	-	-
Boron (B)	15000	LT 2	-	-	-	-	-
Barium (Ba)	18750	LT 2	-	-	-	-	-
Cadmium (Cd)	17	LT 2	-	-	-	-	-
Cobalt (Co)	130	LT 2	-	-	-	-	-
Chromium III (Cr III)	460	LT 0.050	-	-	-	-	-
Chromium VI (Cr VI)	0.2		-	-	-	-	-
Copper (Cu)	7700	LT 2	-	-	-	-	-
Mercury (Hg)	94	LT 2	-	-	-	-	-
Manganese (Mn)	15000	LT 2	-	-	-	-	-
Nickel (Ni)	930	LT 2	-	-	-	-	-
Lead (Pb)	23	LT 2	-	-	-	-	-
Antimony (Sb)	560	LT 2	-	-	-	-	-
Selenium (Se)	460	LT 2	-	-	-	-	-
Tin (Sn)	180000	LT 2	-	-	-	-	-
Organic tin	12	LT 2	-	-	-	-	-
Strontium (Sr)	56000	LT 2	-	-	-	-	-
Zinc (Zn)	46000	LT 2	-	-	-	-	-
Mass of trace amount (gram)			-	-	-	-	-
Conclusion		Pass	-	-	-	-	-

mg/kg = milligrams per kilogram (ppm=parts per million)

* = Average of duplicate analysis

Organic tin = migration of total organic tin is expressed as tributyl tin cation content in mg/kg

= Verified results (see note)

Remark: - Results of Cr III and Cr VI were reported as sum of soluble Chromium content unless specified.

- Result(s) of organic tin was (were) calculated while assuming the tin content wholly contributed from tributyltin cation unless specified.

Note: If soluble chromium content or soluble tin content exceeded the screening limits of soluble chromium (VI) or organic tin content, the results were verified by below method

- Chromium VI: In house Ion-chromatography analysis

- Organic tin: EN71 part 3:2013+A3:2018, Annex G by Gas Chromatography – Mass Spectroscopy analysis.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 57 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Sample Identity	Color	Location	Style
A.	Deep yellow coating	Block	B
B.	Reddish brown / clear coating	Base	B
C.	All coating / white coating	Board & dice	B,D
D.	All coating	Book	F
E.	Purple coating	Block	F
F.	Brown coating	Shape board	F
G.	Shiny silver printed clear plastic	Mirror	A
H.	Flesh plastic	Plastic screw	A
I.	Clear laminated multicolor printed white paper board	Paper Board	B
J.	Clear plastic	End of tie	C,E
K.	Translucent plastic	Zipper teeth	C,E
L.	Flat white plastic	Fastener	C,E
M.	Clear red plastic	Block	F
N.	Clear yellow plastic	Block	F
O.	Clear blue plastic	Block	F
P.	Clear green plastic	Block	F
Q.	Matt white plastic	Shape board & book	F
R.	Bright clear plastic	Spiral of book	F
S.	Deep red fabric / red thread	Fabric	C
T.	Soft orange fabric / orange thread	Fabric	C
U.	Deep green fabric / green thread	Fabric	C
V.	Dull yellow fabric / yellow thread	Fabric	C
W.	Sky blue fabric / blue thread	Pocket	C
X.	Dull blue felt	Pocket	C
Y.	Soft white hook & loop fastener	Velcro	C,E
Z.	Bright white fabric / white thread	Zipper band	C,E



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 58 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Sample Identity	Color	Location	Style
AA.	Matt red felt	Felt	C,E
AB.	Matt yellow felt	Felt	C,E
AC.	Matt green felt	Felt	C
AD.	Matt orange felt	Felt	C
AE.	Deep blue cord	Tie	C
AF.	Lemon yellow cord	Tie	E
AG.	Matt blue felt	Felt	E
AH.	Deep orange felt	Felt	E
AI.	Flat orange fabric	Fabric	E
AJ.	Multicolor printed matt white felt	Felt	E
AK.	Dark green coating	Pattern & logo	A-E
AL.	Light flesh / flesh wood	Wooden board	B-D
AM.	Bright light flesh / bright flesh wood	Wooden board	A,E,F
AN.	Bright red coating	Bright red paint (A1Y)	A-F
AO.	Orange coating	Orange paint (A2Y)	F
AP.	Light yellow coating	Light yellow paint (A3Y)	B,F
AQ.	Light green coating	Light green paint (A6Y)	F
AR.	Dark blue coating	Dark blue paint (A7Y)	A,F
AS.	Light blue coating	Light blue paint (A8Y)	F
AT.	Dark brown coating	Dark brown paint (A10Y)	F
AU.	White coating	White paint (A16Y)	D
AV.	Clear lacquer	Clear lacquer paint (A21Y)	A-F
AW.	Light brown wood	Wooden board	B,D,F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 59 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		A.	B.	C.	D.	E.	F.
Aluminium (Al)	70000	33	15	44	5	9	5
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	3	3	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.59	0.30	0.29	0.60	0.27	0.36
Chromium VI (Cr VI)	0.053	#LT0.0020	#LT0.0020	#LT0.0020	#LT0.0020	#LT0.0020	#LT0.0020
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	4	2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	4	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	2	LT 2	LT 2
Zinc (Zn)	46000	42	100	42	7	9	5
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 60 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		G.	H.	I.	J.	K.	L.
Aluminium (Al)	70000	8	4	160	3	LT 2	2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	LT 0.050	0.11	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.053			#LT0.0020			
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	7	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	20	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 2	2	LT 2	LT 2	LT 2	3
Mass of trace amount (gram)					0.0804		
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 61 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		M.	N.	O.	P.	Q.	R.
Aluminium (Al)	70000	4	7	4	3	2	LT 2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.060	LT 0.050	LT 0.050	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.053	#LT0.0020					
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	12	2	LT 2	LT 2	LT 2	LT 2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 62 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		S.	T.	U.	V.	W.	X.
Aluminium (Al)	70000	3	2	4	3	7	3
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.053	0.053	0.051	LT 0.050	LT 0.050	0.074
Chromium VI (Cr VI)	0.053						#LT0.0020
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	3	4	LT 2	6	LT 2	3
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 2	3	4	LT 2	LT 2	2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 63 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		Y.	Z.	AA.	AB.	AC.	AD.
Aluminium (Al)	70000	LT 2	2	3	3	LT 2	LT 2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	LT 0.050	0.064	0.052	0.055	LT 0.050
Chromium VI (Cr VI)	0.053			#LT0.0020		#LT0.0020	
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	28	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	4	15	LT 2	4
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	LT 2	LT 2	LT 2	71	2	LT 2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 64 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		AE.	AF.	AG.	AH.	AI.	AJ.
Aluminium (Al)	70000	2	3	4	3	LT 2	2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	0.078	0.050	LT 0.050	0.052	LT 0.050	0.064
Chromium VI (Cr VI)	0.053	#LT0.0020					#LT0.0020
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	3	10	11	34
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	4	5	LT 2	50	50	2
Mass of trace amount (gram)							
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 65 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		AK.	AL.	AM.	AN.	AO.	AP.
Aluminium (Al)	70000	10	LT 2	2	LT 2	LT 2	2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Barium (Ba)	18750	LT 2	6	4	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	0.12	LT 0.050	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.053		#LT0.0020				
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	33	4	LT 2	LT 2	LT 2
Nickel (Ni)	930	4	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	2	4	LT 2	LT 2	LT 2
Zinc (Zn)	46000	4	56	21	53	LT 2	140
Mass of trace amount (gram)					0.0856	0.0612	0.0691
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 66 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		AQ.	AR.	AS.	AT.	AU.	AV.
Aluminium (Al)	70000	2	LT 2	LT 2	LT 2	6	LT 2
Arsenic (As)	47	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Boron (B)	15000	LT 2	LT 2	LT 2	6	LT 2	LT 2
Barium (Ba)	18750	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cadmium (Cd)	17	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Cobalt (Co)	130	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Chromium III (Cr III)	460	LT 0.050	LT 0.050	LT 0.050	LT 0.050	LT 0.050	LT 0.050
Chromium VI (Cr VI)	0.053						
Copper (Cu)	7700	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Mercury (Hg)	94	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Manganese (Mn)	15000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Nickel (Ni)	930	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Lead (Pb)	23	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Antimony (Sb)	560	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Selenium (Se)	460	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Tin (Sn)	180000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Organic tin	12	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Strontium (Sr)	56000	LT 2	LT 2	LT 2	LT 2	LT 2	LT 2
Zinc (Zn)	46000	83	97	64	150	96	77
Mass of trace amount (gram)		0.0738	0.0580	0.0781	0.0543	0.0712	0.0806
Conclusion		Pass	Pass	Pass	Pass	Pass	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 67 of 81

RESULTS:

MIGRATION OF CERTAIN ELEMENTS (European Standard EN 71 Part 3: 2019)

Test Method : European Standard EN 71 Part 3: 2019, Section 9.

Class: Category III - Scraped off toy material

Analyte	Requirement (mg/kg)	Result (mg/kg)					
		Sample ID					
		AW.	-	-	-	-	-
Aluminium (Al)	70000	LT 2	-	-	-	-	-
Arsenic (As)	47	LT 2	-	-	-	-	-
Boron (B)	15000	LT 2	-	-	-	-	-
Barium (Ba)	18750	LT 2	-	-	-	-	-
Cadmium (Cd)	17	LT 2	-	-	-	-	-
Cobalt (Co)	130	LT 2	-	-	-	-	-
Chromium III (Cr III)	460	LT 0.050	-	-	-	-	-
Chromium VI (Cr VI)	0.053						
Copper (Cu)	7700	LT 2	-	-	-	-	-
Mercury (Hg)	94	LT 2	-	-	-	-	-
Manganese (Mn)	15000	LT 2	-	-	-	-	-
Nickel (Ni)	930	LT 2	-	-	-	-	-
Lead (Pb)	23	LT 2	-	-	-	-	-
Antimony (Sb)	560	LT 2	-	-	-	-	-
Selenium (Se)	460	LT 2	-	-	-	-	-
Tin (Sn)	180000	LT 2	-	-	-	-	-
Organic tin	12	LT 2	-	-	-	-	-
Strontium (Sr)	56000	LT 2	-	-	-	-	-
Zinc (Zn)	46000	LT 2	-	-	-	-	-
Mass of trace amount (gram)			-	-	-	-	-
Conclusion		Pass	-	-	-	-	-

mg/kg = milligrams per kilogram (ppm=parts per million)

* = Average of duplicate analysis

Organic tin = migration of total organic tin is expressed as tributyl tin cation content in mg/kg

= Verified results (see note)

LT = Less Than

FR = Failed Result

Remark: - Results of Cr III and Cr VI were reported as sum of soluble Chromium content unless specified.
- Result(s) of organic tin was (were) calculated while assuming the tin content wholly contributed from tributyltin cation unless specified.

Note:

If soluble chromium content or soluble tin content exceeded the screening limits of soluble chromium (VI) or organic tin content, the results were verified by below method

- Chromium VI: EN71 part 3:2019, Annex F
- Organic tin: EN71 part 3:2019, Annex G by Gas Chromatography – Mass Spectroscopy analysis.



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 68 of 81

RESULTS:

BBP/DBP/DEHP CONTENTS IN TOYS AND CHILDCARE ARTICLES (European Regulation (EC)

No. 1907/2006 REACH Annex XVII, Item no. 51)

Test Method: With referenced to EN 14372:2004 Section 6.3.2, sample was extracted with organic solvent and then analyzed by Gas Chromatograph Mass Spectrometer

Sample Identity	Test Component	Location	Style
A.	Deep yellow coating Reddish brown / clear coating All coating / white coating	Block Base Board & dice	B B B,D
B.	All coating Purple coating Brown coating	Book Block Shape board	F F F
C.	Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E
D.	Shiny silver printed clear plastic Flesh plastic Clear laminated multicolor printed white paper board	Mirror Plastic screw Paper Board	A A B
E.	Clear plastic Translucent plastic Flat white plastic	End of tie Zipper teeth Fastener	C,E C,E C,E
F.	Clear red plastic Clear yellow plastic Clear blue plastic	Block Block Block	F F F
G.	Clear green plastic Matt white plastic Bright clear plastic	Block Shape board & book Spiral of book	F F F
H.	Bright red coating	Bright red paint (A1Y)	A-F
I.	Orange coating	Orange paint (A2Y)	F
J.	Light yellow coating	Light yellow paint (A3Y)	B,F
K.	Dark green coating	Dark green paint (A5Y)	A-E
L.	Light green coating	Light green paint (A6Y)	F
M.	Dark blue coating	Dark blue paint (A7Y)	A,F
N.	Light blue coating	Light blue paint (A8Y)	F
O.	Dark brown coating	Dark brown paint (A10Y)	F
P.	White coating	White paint (A16Y)	D
Q.	Clear lacquer	Clear lacquer paint (A21Y)	A-F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 69 of 81

RESULTS:

BBP/DBP/DEHP CONTENTS IN TOYS AND CHILDCARE ARTICLES (European Regulation (EC)

No. 1907/2006 REACH Annex XVII, Item no. 51)

Test Method: With referenced to EN 14372:2004 Section 6.3.2, sample was extracted with organic solvent and then analyzed by Gas Chromatograph Mass Spectrometer

Test Parameter:	BBP	DBP	DEHP	Sum of three phthalates	
Limit (%):	0.1	0.1	0.1	0.1	
Sample	Result (%)				Conclusion
A.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
B.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
C.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
D.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
E.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
F.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
G.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
H.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
I.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
J.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
K.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
L.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
M.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
N.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
O.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
P.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
Q.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS

Detection Limit :

BBP = Butyl benzyl phthalate (0.005%)

DBP = Dibutyl phthalate (0.005%)

DEHP = Di(2-ethylhexyl) phthalate (0.005%)

Results reported in percentage

LT = Less than

ND = None detected



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 70 of 81

RESULTS:

DNOP/DINP/DIDP CONTENTS IN TOYS AND CHILDCARE ARTICLES WHICH CAN BE PLACED IN MOUTH BY THE CHILDREN (European Regulation (EC) No. 1907/2006 REACH Annex XVII, Item no. 52)

Test Method: With referenced to EN 14372:2004 Section 6.3.2, sample was extracted with organic solvent and then analyzed by Gas Chromatograph Mass Spectrometer

Sample Identity	Test Component	Location	Style
A.	Deep yellow coating Reddish brown / clear coating All coating / white coating	Block Base Board & dice	B B B,D
B.	All coating Purple coating Brown coating	Book Block Shape board	F F F
C.	Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E
D.	Shiny silver printed clear plastic Flesh plastic Clear laminated multicolor printed white paper board	Mirror Plastic screw Paper Board	A A B
E.	Clear plastic Translucent plastic Flat white plastic	End of tie Zipper teeth Fastener	C,E C,E C,E
F.	Clear red plastic Clear yellow plastic Clear blue plastic	Block Block Block	F F F
G.	Clear green plastic Matt white plastic Bright clear plastic	Block Shape board & book Spiral of book	F F F
H.	Bright red coating	Bright red paint (A1Y)	A-F
I.	Orange coating	Orange paint (A2Y)	F
J.	Light yellow coating	Light yellow paint (A3Y)	B,F
K.	Dark green coating	Dark green paint (A5Y)	A-E
L.	Light green coating	Light green paint (A6Y)	F
M.	Dark blue coating	Dark blue paint (A7Y)	A,F
N.	Light blue coating	Light blue paint (A8Y)	F
O.	Dark brown coating	Dark brown paint (A10Y)	F
P.	White coating	White paint (A16Y)	D
Q.	Clear lacquer	Clear lacquer paint (A21Y)	A-F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 71 of 81

RESULTS:

DNOP/DINP/DIDP CONTENTS IN TOYS AND CHILDCARE ARTICLES WHICH CAN BE PLACED IN MOUTH BY THE CHILDREN (European Regulation (EC) No. 1907/2006 REACH Annex XVII, Item no. 52)

Test Method: With referenced to EN 14372:2004 Section 6.3.2, sample was extracted with organic solvent and then analyzed by Gas Chromatograph Mass Spectrometer

Test Parameter:	DNOP	DINP	DIDP	Sum of three phthalates	
Limit (%):	0.1	0.1	0.1	0.1	
Sample	Result (%)				Conclusion
A.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
B.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
C.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
D.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
E.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
F.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
G.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
H.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
I.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
J.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
K.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
L.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
M.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
N.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
O.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
P.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS
Q.	LT 0.005	LT 0.005	LT 0.005	LT 0.015	PASS

Detection Limit :

DNOP = Di-n-octyl phthalate (0.005%)

DINP = Di-iso-nonyl phthalate (0.005%)

DIDP = Di-iso-decyl phthalate (0.005%)

Results reported in percentage

LT = Less than

ND = None detected



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 72 of 81

RESULTS:

BBP/DBP/DEHP/DIBP CONTENTS (European Regulation (EC) No. 1907/2006 REACH Annex XVII, Item no. 51 (amended up to EU No. 2018/2005))

Test Method: With referenced to EN 14372:2004 Section 6.3.2, sample was extracted with organic solvent and then analyzed by Gas Chromatograph Mass Spectrometer

Sample Identity	Test Component	Location	Style
A.	Deep yellow coating Reddish brown / clear coating All coating / white coating	Block Base Board & dice	B B B,D
B.	All coating Purple coating Brown coating	Book Block Shape board	F F F
C.	Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E
D.	Shiny silver printed clear plastic Flesh plastic Clear laminated multicolor printed white paper board	Mirror Plastic screw Paper Board	A A B
E.	Clear plastic Translucent plastic Flat white plastic	End of tie Zipper teeth Fastener	C,E C,E C,E
F.	Clear red plastic Clear yellow plastic Clear blue plastic	Block Block Block	F F F
G.	Clear green plastic Matt white plastic Bright clear plastic	Block Shape board & book Spiral of book	F F F
H.	Bright red coating	Bright red paint (A1Y)	A-F
I.	Orange coating	Orange paint (A2Y)	F
J.	Light yellow coating	Light yellow paint (A3Y)	B,F
K.	Dark green coating	Dark green paint (A5Y)	A-E
L.	Light green coating	Light green paint (A6Y)	F
M.	Dark blue coating	Dark blue paint (A7Y)	A,F
N.	Light blue coating	Light blue paint (A8Y)	F
O.	Dark brown coating	Dark brown paint (A10Y)	F
P.	White coating	White paint (A16Y)	D
Q.	Clear lacquer	Clear lacquer paint (A21Y)	A-F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 73 of 81

RESULTS:

BBP/DBP/DEHP/DIBP CONTENTS (European Regulation (EC) No. 1907/2006 REACH Annex XVII, Item no. 51 (amended up to EU No. 2018/2005))

Test Method: With referenced to EN 14372:2004 Section 6.3.2, sample was extracted with organic solvent and then analyzed by Gas Chromatograph Mass Spectrometer

Test Parameter:	BBP	DBP	DEHP	DIBP	Sum of four phthalates	
Limit (%):	0.1	0.1	0.1	0.1	0.1	
Sample	Result (%)					Conclusion
A.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
B.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
C.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
D.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
E.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
F.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
G.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
H.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
I.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
J.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
K.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
L.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
M.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
N.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
O.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
P.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS
Q.	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.020	PASS

Detection Limit :

BBP = Butyl benzyl phthalate (0.005%)

DBP = Dibutyl phthalate (0.005%)

DEHP = Di(2-ethylhexyl) phthalate (0.005%)

DIBP = Diisobutyl phthalate (0.005%)

Results reported in percentage

LT = Less than

ND = None detected



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 74 of 81

RESULTS:

PHthalates Content in Children's Toys and Child Care Articles (Consumer Product Safety Improvement Act (CPSIA) of 2008, Section 108(a) and 108(c), 16 CFR 1307)

Test Method: With reference to U. S. CPSC-CH-C1001-09.3 (April 1, 2010) / CPSC-CH-C1001-09.4 (January 17, 2018).

Sample Identity	Color / Component	Location	Style
A.	Deep yellow coating Reddish brown / clear coating All coating / white coating	Block Base Board & dice	B B B,D
B.	All coating Purple coating Brown coating	Book Block Shape board	F F F
C.	Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E
D.	Shiny silver printed clear plastic Flesh plastic Clear laminated multicolor printed white paper board	Mirror Plastic screw Paper Board	A A B
E.	Clear plastic Translucent plastic Flat white plastic	End of tie Zipper teeth Fastener	C,E C,E C,E
F.	Clear red plastic Clear yellow plastic Clear blue plastic	Block Block Block	F F F
G.	Clear green plastic Matt white plastic Bright clear plastic	Block Shape board & book Spiral of book	F F F
H.	Bright red coating	Bright red paint (A1Y)	A-F
I.	Orange coating	Orange paint (A2Y)	F
J.	Light yellow coating	Light yellow paint (A3Y)	B,F
K.	Dark green coating	Dark green paint (A5Y)	A-E
L.	Light green coating	Light green paint (A6Y)	F
M.	Dark blue coating	Dark blue paint (A7Y)	A,F
N.	Light blue coating	Light blue paint (A8Y)	F
O.	Dark brown coating	Dark brown paint (A10Y)	F
P.	White coating	White paint (A16Y)	D
Q.	Clear lacquer	Clear lacquer paint (A21Y)	A-F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 75 of 81

RESULTS:

PHthalATES CONTENT IN CHILDREN'S TOYS AND CHILD CARE ARTICLES (Consumer Product Safety Improvement Act (CPSIA) of 2008, Section 108(a) and 108(c), 16 CFR 1307)

Test Method: With reference to U. S. CPSC-CH-C1001-09.3 (April 1, 2010) / CPSC-CH-C1001-09.4 (January 17, 2018).

Test Parameter:	Listed Phthalates (See Remark)		
Requirement:	Each 0.1%		
Sample ID	Detected Analyte	Concentration (%)	Conclusion
A.	ND	ND	PASS
B.	ND	ND	PASS
C.	ND	ND	PASS
D.	ND	ND	PASS
E.	ND	ND	PASS
F.	ND	ND	PASS
G.	ND	ND	PASS
H.	ND	ND	PASS
I.	ND	ND	PASS
J.	ND	ND	PASS
K.	ND	ND	PASS
L.	ND	ND	PASS
M.	ND	ND	PASS
N.	ND	ND	PASS
O.	ND	ND	PASS
P.	ND	ND	PASS
Q.	ND	ND	PASS

Results reported in percentage

ND = None detected

Detection Limit: Each Phthalate (0.005%)

LIST OF RESTRICTED PHthalATES		
Number	Chemical Name	CAS Number
1.	Butyl benzyl phthalate (BBP)	85-68-7
2.	Dibutyl phthalate (DBP)	84-74-2
3.	Di(2-ethylhexyl) phthalate (DEHP)	117-81-7
4.	Di-iso-nonyl phthalate (DINP)	28553-12-0 & 68515-48-0
5.	Di-iso-butyl phthalate (DIBP)	84-69-5
6.	Di-n-pentyl phthalate (DPENP or DnPP)	131-18-0
7.	Di-n-hexyl phthalate (DHEXP or DnHP)	84-75-3
8.	Dicyclohexyl phthalate (DCHP)	84-61-7

RESULTS:

CLIENT'S 17 PHTHALATES CONTENT SPECIFICATION

• **BBP/DBP/DEHP/DNOP/DINP/DIDP Content**

Color / Component	Location	Style
A. Composite of Deep yellow coating Reddish brown / clear coating All coating / white coating	Block Base Board & dice	B B B,D
B. All coating Purple coating Brown coating	Book Block Shape board	F F F
C. Soft blue coating Dull orange coating Deep red coating	Fastener Fastener Fastener	C C E
D. Shiny silver printed clear plastic Flesh plastic Clear laminated multicolor printed white paper board	Mirror Plastic screw Paper Board	A A B
E. Clear plastic Translucent plastic Flat white plastic	End of tie Zipper teeth Fastener	C,E C,E C,E
F. Clear red plastic Clear yellow plastic Clear blue plastic	Block Block Block	F F F
G. Clear green plastic Matt white plastic Bright clear plastic	Block Shape board & book Spiral of book	F F F
H. Bright red coating	Bright red paint (A1Y)	A-F
I. Orange coating	Orange paint (A2Y)	F
J. Light yellow coating	Light yellow paint (A3Y)	B,F
K. Dark green coating	Dark green paint (A5Y)	A-E
L. Light green coating	Light green paint (A6Y)	F
M. Dark blue coating	Dark blue paint (A7Y)	A,F
N. Light blue coating	Light blue paint (A8Y)	F
O. Dark brown coating	Dark brown paint (A10Y)	F
P. White coating	White paint (A16Y)	D
Q. Clear lacquer	Clear lacquer paint (A21Y)	A-F



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 77 of 81

RESULTS:

CLIENT'S 17 PHTHALATES CONTENT SPECIFICATION

• BBP/DBP/DEHP/DNOP/DINP/DIDP Content

Test Parameter	BBP	DBP	DEHP	DNOP	DINP	DIDP	
Limit (%)	0.1	0.1	0.1	0.1	0.1	0.1	
Sample	Result (%)						Conclusion
A	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
B	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
C	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
D	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
E	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
F	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
G	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
H	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
I	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
J	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
K	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
L	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
M	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
N	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
O	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
P	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
Q	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass

Detection Limit :

DNOP = Di-n-octyl phthalate (0.005%) 117-84-0

DINP = Di-iso-decyl phthalate (0.005%) 26761-40-0 / 68515-49-1

BBP = Butyl benzyl phthalate (0.005%) 85-68-7

DBP = Dibutyl phthalate (0.005%) 84-74-2

DEHP = Di(2-ethylhexyl) phthalate (0.005%) 117-81-7

Results reported in percentage

LT = Less than

ND = None detected



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 79 of 81

RESULTS:

CLIENT'S 17 PHTHALATES CONTENT SPECIFICATION

- **EC No. 201-559-5 / DiBP / DHNUP / DIHP / DMEP / DIPP / DnPP / DPP / PiPP / DHP / 1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear Content**

Test Parameter	DnPP	DPP	PiPP	DHP	1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear	
Limit (%)	0.1	0.1	0.1	0.1	0.1	
Sample						Conclusion
A	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
B	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
C	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
D	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
E	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
F	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
G	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
H	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
I	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
J	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
K	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
L	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
M	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
N	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
O	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
P	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass
Q	LT 0.005	LT 0.005	LT 0.005	LT 0.005	LT 0.005	Pass



CARPENTERS MANUFACTORY LIMITED

Technical Report: **(8520)020-0189**

March 17, 2020

Page 80 of 81

RESULTS:

CLIENT'S 17 PHTHALATES CONTENT SPECIFICATION

Results reported in percentage

LT = Less than

ND = None detected

Detection Limit:

DiBP = Diisobutylphthalate 84-69-5

*DHNUP = 1,2-Benzenedicarboxylic acid, di-C7, 11-
branched and linear alkyl esters 68515-42-4*

*DIHP = 1,2-Benzenedicarboxylic acid, di-C6-8-branched
alkyl esters, C7-rich 71888-89-6*

DMEP = Dimethoxyethyl phthalate 117-82-8

DIPP = Diisopentylphthalate 605-50-5

DnPP = Dipentylphthalate 131-18-0

*DPP = 1,2-benzenedicarboxylic acid dipentylester,
branched and linear 84777-06-0*

PiPP = n-Pentyl-Isopentylphthalate 776297-69-9

DHP = Dihexylphthalate 84-75-3

*1,2-Benzenedicarboxylic acid, dihexyl ester, branched and
linear 68515-50-4*

*EC No. 201-559-5 = 1,2-benzenedicarboxylic acid, di-C6-
10-alkyl esters; 1,2-benzenedicarboxylic
acid, mixed decyl and hexyl and octyl
diesters with $\geq 0.3\%$ of dihexyl phthalate
68515-51-5 / 68648-93-1*

RESULTS:



Sample Number
85200200189A1



Sample Number
85200200189B1



Sample Number
85200200189C1



Sample Number
85200200189D1



Sample Number
85200200189E1



Sample Number
85200200189F1

END OF REPORT